

530 nm band PANDA

Feature

- 530 nm band polarization maintaining fiber

Common specifications

| | |
|------------------------|---|
| Concentricity error | ≤ 0.5 μm |
| Cladding diameter | 125 ± 1 μm (Major diameter) |
| Polarization crosstalk | ≤ -30 dB/100m @ 630 nm |
| Beat length | ≤ 2.0 mm @ 630 nm |
| Minimum bending radius | 1% proof : R30 mm* 2% proof : R20 mm |

Product list (Underlined product is new model)

| Product | Mode field diameter | Attenuation | Cutoff wavelength | Coating structure | Coating diameter |
|---------------------|--------------------------|------------------------|-------------------|--|------------------|
| <u>SM53-PS-H90D</u> | 4.2 ± 0.5 μm @ 630 nm | ≤ 15 dB/km @ 630 nm | 0.45 - 0.53 μm | UV curable acrylate /Polyester elastomer (Color : Black) | 900 ± 100 μm |
| <u>SM53-PS-U40D</u> | | | | UV curable acrylate | 400 ± 15 μm |

*1% proof test type is standard. 2% proof test type is available, and code '-H' is added at the end of the product name. (e.g. SM15-PS-U40D-H)



Optical Fiber Division
1440, Mutsuzaki, Sakura, Chiba 285-8550, Japan

<http://www.fujikura.co.jp/>
optodevice@jp.fujikura.com

Specifications are subject to change without prior notice